

检 验 报 告

TEST REPORT

试样名称	汇流排
PRODUCT NAME:	Busbar
规格型号	3P
TYPE/MODEL:	3P
委托单位	卡尔科技有限公司
CUSTOMER:	CHEAR Technology Co., Ltd
检验类别	委托检验
TEST KIND:	Sample test



苏州美标检测技术有限公司检测中心

Suzhou ASTTEK Testing Technology Co., Ltd IQ Center



In no circumstances shall the company is responsibility extend beyond inspection, testing and reporting upon the samples actually drawn from the bulk and inspected tested and at the sole and exclusive responsibility of the Principal. This test report cannot be reproduced except in full.

检 验 报 告

TEST REPORT

试样名称 PRODUCT NAME	汇流排		
	Busbar		
型号规格 TYPE/MODEL	3P		
	3P		
检验类别 TEST KIND	委托检验	检验编号 CHECK NUMBER	SZ20042202A
	Sample test		
委托单位 CUSTOMER	卡尔科技有限公司	单位地址 UNIT ADDRESS	浙江省乐清经济开发区纬二十路 230 号
	CHEAR Technology Co., Ltd.		No. 230, Wei 20 road, Yueqing Economic Development Zone, Zhejiang Province
生产单位 MANUFACTU RER	---	到样日期 SAMPLE DATE	2020.04.17

取样方式 RECEIPT	寄送	电话号码 TEL.	13777735755
	Post		
检验依据 TEST STANDARD	UL94 《设备和器具部件塑料材料燃烧测试》		
	UL94 《Test for Flammability of Plastic Materials for Parts in Devices and Appliances》		
检验日期 TEST DATE	2020.04.18-2020.04.22		
检验结论 CONCLUSION	样品测试结果符合UL94 V-0要求。		
	The test result meet the requirements of V-0 in UL94.		
编写 REPORT MAKER	刘年	审核 CHECK	吴伟
			批准 APPROVAL

In no circumstances shall the company is responsibility extend beyond inspection, testing and reporting upon the samples actually drawn from the bulk and inspected tested and at the sole and exclusive responsibility of the Principal. This test report cannot be reproduced except in full.

检 验 结 果

TEST RESULTS

序号 Serial No.	检验项目 Test Items	单位 Unit	标准要求 Standard requirement	检验结果 Test result					判断 Judgement
1.0	样品描述 Description								
	颜色 color	-	-	白色					-
	长度 length	mm	125±5	125.5					P
	宽度 width	mm	13±0.5	13.2					P
	厚度 thickness	mm	≤13	1.0					P
1.1	实验条件 Experiment condition								
	温度 Temperature	℃	23±2	24					P
	湿度 Humidity	%	50±5	53					P
	时间 Time	H	≥48	48					P
1.2	样品测试 Sample test								
	余焰时间 Afterflame time t1	s	≤10s	0.6	0.7	0.6	0.6	0.5	P
	余焰时间 Afterflame time t2	s	≤10s	1.0	1.0	1.1	1.0	1.1	P
	余灼时间 Afterglow time t3	s	-	0.1	0.2	0.2	0.3	0.2	-
	单个样品 Single sample t2+t3	s	≤30s	1.1	1.2	1.3	1.3	1.3	P
	所有样品 5 samples t1+t2	s	≤50s	8.2					P
	火焰蔓延至夹具 flame or glow spread to the holding clamp	-	N	N	N	N	N	N	P
	引燃脱脂棉 Cotton indicator ignited	-	N	N	N	N	N	N	P
1.3	判定等级 Judgment	-	V-0	V-0					P


单项判断”符号含义：P：检验结果符合要求；F：检验结果不符合要求；N：结果不发生；Y：结果发生-：无内容。
 “P” represents pass; “F” represents failure; “N” represents not happen; “Y” represents yes “-” represents no content.

In no circumstances shall the company is responsibility extend beyond inspection, testing and reporting upon the samples actually drawn from the bulk and inspected tested and at the sole and exclusive responsibility of the Principal. This test report cannot be reproduced except in full.

样品图片

SAMPLE PICTURES

样品图片
Sample picture



实验图片
Pictures after the experiment



In no circumstances shall the company is responsibility extend beyond inspection, testing and reporting upon the samples actually drawn from the bulk and inspected tested and at the sole and exclusive responsibility of the Principal. This test report cannot be reproduced except in full.

声 明

STATEMENT

1. 我司承诺所有的测试数据都保证真实有效，如客户对测试结果有疑义，可以在一周内提出复检。

We promise all the test data are correct and true, the client can request re-test within one week, if doubting the test result.

2. 我司将对客户所有的产品信息进行保密，绝不泄露。

All the information for the samples will be protected by us ,no any will be leaked out.

3. 所测试的样品可以在实验室保存一周，之后将根据实验室的规定进行销毁处理。

The samples can be kept in our lab for one week, later it will be disposed based on the regulation of the Lab.

4. 测试的结果仅作为参照，我们不对除样品外的产品负责。

The test result of the samples are the reference only, we are not responsible for other products.

5. 如有争端，客户可以委托苏州仲裁委员会进行处理。

When disputing, the client can request Suzhou arbitration commission to handle it.

In no circumstances shall the company is responsibility extend beyond inspection, testing and reporting upon the samples actually drawn from the bulk and inspected tested and at the sole and exclusive responsibility of the Principal. This test report cannot be reproduced except in full.